

exena.

BORNEO_24 S3L FO SR



DESCRIERE	NORMA EN ISO 20345:2022 + A1:2024		REZULTAT	CERINTE
FETE: Piele intoarsa, hidrofobizata	5.4.3 Rezistenta la sfasiere		205 N	≥120 N
	5.4.6 Permeabilitatea vaporilor de apa Coeficient		4,5 mg/cm ² h	≥ 0,8 mg/cm ² h
CAPTUSEALA CAPUTA: Respirabila, rezistenta la abraziune	5.5.2 Rezistenta la sfasiere		38,1 mg/cm ²	≥15,0 mg/cm ²
	5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (Uscat)		46 N	≥ 15 N
	Permeabilitatea vaporilor de apa Coeficient		No holes	25.600 cycles
			No holes	51.200 cycles
			66.2 mg/cm ² h	≥ 2,0 mg/cm ²
			530,1 mg/cm ²	≥20,0 mg/cm ²
CAPTUSEALA STAIF: Respirabila, rezistenta la abraziune	5.5.1 Rezistenta la sfasiere		51 N	≥ 15 N
	5.5.2 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat)		No holes	25.600 cycles
	Permeabilitatea vaporilor de apa Coeficient		No holes	51.200 cycles
			68,6 mg/cm ² h	≥ 2,0 mg/cm ²
			549,6 mg/cm ²	≥20,0 mg/cm ²
CAPTUSEALA:	5.5.2 Rezistenta la sfasiere		51 N	≥ 15 N
	5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat)		No holes	25.600 cycles
	Permeabilitatea vaporilor de apa Coeficient		No holes	51.200 cycles
			68,6 mg/cm ² h	≥ 2,0 mg/(cm ² h)
			549,6 mg/cm ²	≥20,0 mg/cm ²
BOMBEU:	Rezistenta la impact	15.5	≥ 14 mm	
Nemetalic, din policarbonat	Rezistenta la compresiune	15,5	≥ 14 mm	

EXENA SRL
via Breda 20
62012 Civitanova M. MC
ITALY

REA MC144207
Reg. Impr. Trib. MC 01336080435
C.F. e P. IVA 01336080435
Cap. Soc. € 25.823,00 i.v.

+39 0733 89 72 56
info@exena.com
amministrazione@pec.exena.it

exena.com

LAMELA ANTIPERFORATIE: Nemetalica, de tip "L"	6.2.1.1.3 Resistenta la penetrare	PASS	Min.1100 N
BRANT: Detasabil, cushione, antistatic.	5.7.4.2 Rezistenta la abraziune	NO HOLES	25.600 cycles
	(uscata) Rezistenta la abraziune (umed)	NO HOLES	12.800 cycles
TALPA: PU PU 2D, SR	5.8.3 Rezistenta la sfasiere		
	5.8.4 Rezistenta la abraziune	11 kN/m	≥ 8 kN/m
	5.8.5 Rezistenta la flexare	52 mm ³	≤ 150 mm ³
	5.8.6 Hidroliza	1 mm	≤ 4,0 mm
	6.4.2 Rezistenta la uleiuri	1,3 mm	≤ 6,0 mm
		6,8 %	≤ 12%
	6.2.10 Rezistenta la alunecare pe placi ceramice acoperite cu glicerina (inclinat spre calcai la 7°)	0,23	≥ 0,19
	(inclinat spre calcai la 7°)	0,26	≥ 0,22
	5.3.5.2 Rezistenta la alunecare pe placi de otel spalate cu detergent (inclinat spre calcai la 7°)	0,36	≥ 0,31
	(inclinat spre calcai la 7°)	0,41	≥ 0,36
	6.2.2.2 Antistatic	uscata: 821 MΩ umed: 551 MΩ	0,1 ÷ 1000 MΩ 0,1 ÷ 1000 MΩ

MARIMI: 35-48

GREUTATE: 1.2 kg (1 pa 42)