

FLEXOR S1 PL FO SC SR ESD



DESCRIZIONE	NORMA EN ISO 20345:2022 + A1:2024	REZULTAT	CERINTA
FETE: Piele intoarsa si material textil respirabil	5.4.3 Rezistenta la rupere 5.4.6 Permeabilitatea vaporilor de apa Coeficient	65 N 4,6 mg/cm2h 38,1 mg/cm2	≥120 N ≥ 0,8 mg/cm2h ≥ 15,0 mg/cm2
CAPTUSEALA CAPUTA: Material textil respirabil, rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (Umed) Rezistenta la abraziune (Uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	96 N No holes No holes 23,6 mg/cm2h 188,9 mg/cm2	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm2 ≥20,0 mg/cm2
CAPTUSEALA STAIF: Material textil respirabil, rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (Umed) Rezistenta la abraziune (Uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	32 N No holes No holes 126,4 mg/cm2h 1011,6 mg/cm2	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm2 ≥20,0 mg/cm2
CAPTUSEALA: Material textil respirabil, rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (Umed) Rezistenta la abraziune (Uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	32 N No holes No holes 15,2 mg/cm2h 122,6 mg/cm2	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/(cm2h) ≥20,0 mg/cm2
BOMBEU: Nemetalic din fibra de sticla, rezistent la 200J	5.3.2.6 Rezistenta la impact 5.3.2.7 Rezistenta la compresie	16,0 mm 16,0 mm	≥ 14 mm ≥ 14 mm

REZISTENTA LA PERFORARE: Material antiperforatie clasa PL				6.2.1.1.3 Rezistenta la perforare				PASS			Min.1100 N		
ACOPERIS DE BRANT: Detasabil, respirabil, antistatic				5.7.4.2 Rezistenta la abraziune (uscat) Rezistenta la abraziune (umed)				NO HOLES NO HOLES			25.600 cicluri 12.800 cicluri		
TALPA EXTERIOARA: Poliuretan 3D tripla densitate cu insertie Etpu				5.8.3 Rezistenta la rupere				8,4 kN/m			≥ 8 kN/m		
				5.8.4 Rezistenta la abraziune				77 mm3			≤ 150 mm3		
				5.8.5 Rezistenta la flexare				2,1 mm			≤ 4,0 mm		
				5.8.6 Hidroliza				2,5 mm			≤ 6,0 mm		
				6.4.2 Rezistenta la uleiuri				1,3 %			≤ 12%		
				6.2.10 Rezistenta la alunecare pe placi ceramice cu glicerina									
				(inclinat spre calcai la 7 grade)				0,22			≥ 0,19		
				(inclinat spre varf la 7 grade)				0,25			≥ 0,22		
				5.3.5.2 Rezistenta la alunecare pe placi ceramice cu agent de curatare									
				(inclinat spre calcai la 7 grade)				0,34			≥ 0,31		
(inclinat spre varf la 7 grade)				0,39			≥ 0,36						
6.2.2.2 Antistatic							uscat: 51,8 MΩ			0,1 ÷ 1000 MΩ			
							umed: 5,87 MΩ			0,1 ÷ 1000 MΩ			
MARIMI: 35-48													
GREUTATE:													
35	36	37	38	39	40	41	42	43	44	45	46	47	48
700	759	818	877	936	995	1054	1113	1172	1231	1290	1349	1408	1467