MONZA_18 S1P SRC

DESCRIPTION	NORMA EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Suede leather	5.4.3 Tear strength	208 N	≥120 N
	5.4.6 Water vapor permeability	1,3 mg/cm²h	≥ 0,8 mg/cm²h
	Coefficient	18,6 mg/cm²	≥ 15,0 mg/cm²
VAMP LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	45 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
	5.5.3 Water vapor permeability	4,7 mg/cm²h	≥ 2,0 mg/cm²
	Coefficient	40,5 mg/cm²	≥20,0 mg/cm²
QUARTER LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	25 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No holes	51.200 cycles
	Abrasion resistance(Dry)	No holes	25.600 cycles
	5.5.3 Water vapor permeability	11,3 mg/cm²h	≥ 2,0 mg/cm²
	Coefficient	90,6 mg/cm²	≥20,0 mg/cm²
SAFETY TOE CAP: Steel	5.3.2.3 Impact resistance	14,5 mm	≥ 14 mm
	5.3.2.4 Compression resistance	15 mm	≥ 14 mm
PIERCE-RESISTANCE: Stainless steel	5.7.1. Thickness	2,5 mm	≥ 2,0 mm
	5.7.3 Water absorption	85 mg/cm²	≥70,0 mg/cm²
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
OUTSOLE: PU 1D, Antislip sole, SRC	5.8.2 Tear strength	10,6 kN/m	≥ 8 kN/m
	5.8.3 Abrasion resistance	59 mm³	≤ 150 mm³
	5.8.4 Flexing resistance	2,0 mm	≤ 4,0 mm
	5.8.5 Hydrolysis	1,0 mm	≤ 6,0 mm
	6.4.2 Oils resistance	1.0 %	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,40	≥ 0,32
	Heel slip	0,39	≥ 0,28
	Stainless steel plate on glycerin resistance		
	Flat slip	0,22	≥ 0,18
	Heel slip	0,18	≥ 0,13

MISURE : 35-48

EXENA S.r.l.
Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519
C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207
www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it