

STARDUST S1P SRC ESD



DESCRIERE	NORMA EN ISO 20345:2011	REZULTAT	CERINTE
FETE: Piele intorsa si material si material textil	5.4.3 Rezistenta la rupere 5.4.6 Permeabilitatea vaporilor de apa Coeficient	106 N 103,3 mg/cm ² h 826,7 mg/cm ²	≥60 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
CAPTUSEALA CAPUSA: Respirabila, rezistenta la abraziune.	5.5.1 Rezistenta la rupere 5.5.2 Rezistenta la abraziune(umed) Rezistenta la abraziune(uscat)	42 N Fara gauri 139,2 mg/cm ² h 1113,9 mg/cm ²	≥ 15 N 25.600 cycles 12.800 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
CAPTUSELA STAIF: Respirabila, rezistenta la abraziune.	5.5.3 Permeabilitatea vaporilor de apa Coeficient 5.5.1 Rezistenta la rupere 5.5.2 Rezistenta la abraziune(umed) Rezistenta la abraziune(uscat)	32 N Fara gauri	≥ 15 N 51.200 cycles 25.600 cycles
CAPTUSEALA: Respirabila, rezistenta la abraziune.	5.5.3 Permeabilitatea vaporilor de apa Coeficient 5.5.1 Rezistenta la rupere 5.5.2 Rezistenta la abraziune(umed) Rezistenta la abraziune(uscat)	126.4 mg/cm ² h 1011,6 mg/cm ² 33 N Fara gauri Fara gauri 15,2 mg/cm ² h	≥ 2,0 mg/cm ² ≥20,0 mg/cm ² ≥ 15 N 51.200 cycles 25.600 cycles ≥ 2,0 mg/cm ²
BOMBEU: Nemetalic, din policarbonat	5.3.2.3 Rezistenta la impact 5.3.2.4 Rezistenta la compresiune	122 mg/cm ² 17,0 mm 19,0 mm	≥20,0 mg/cm ² ≥ 14 mm ≥ 14 mm
LAMELA ANTIPERFORATIE: Nemetalica	5.7.1. Grosime 5.7.3 Absorbția apei	3,5 mm 88 mg/cm ²	≥ 2,0 mm ≥70,0 mg/cm ²
ACOPERIS BRANT: Detasabil, respirabil, antistatic.	5.7.4.2 Rezistenta la abraziune(umed) Rezistenta la abraziune(uscat)	Fara gauri Fara gauri	25.600 cicluri 12.800 cicluri
Impamantare	6.3 Rezistenta la impamantare 6.4 Incarcarea 7.0 Rezistenta electrica	42 Dx = 1,60 x 10 ⁸ Ω 42 Sx = 1,54 x 10 ⁸ Ω 42 Dx = 9,82 x 10 ⁷ Ω 42 Sx = 9,62 x 10 ⁷ Ω 42= 10,77V	<1,00 x 10 ⁹ Ω <1,00 x 10 ⁹ Ω <100V

TALPA: PU 2D antislip, SRC	5.8.2 Resistenza la rupere	14,9 kN/m	$\geq 8 \text{ kN/m}$
	5.8.3 Resistenza la abraziune	142 mm ³	$\leq 150 \text{ mm}^3$
	5.8.4 Resistenza la flexare	0,5 mm	$\leq 4,0 \text{ mm}$
	5.8.5 Hidroliza	0,6 mm	$\leq 6,0 \text{ mm}$
	5.10 Antistatic	dry: $8,59 \times 10^7 \Omega$ wet: $4,35 \times 10^7 \Omega$	
	6.4.2 Resistenza la uleiuri	2,4 %	$\leq 12\%$
	5.11 Resistenta pe placi ceramice Spalate cu detergent		
	Alunecare pe talpa	0,56	$\geq 0,32$
	Alunecare pe calcai	0,35	$\geq 0,28$
	Rezistenta pe placi ceramice		
acoperite cu glicerina	Alunecare pe talpa	0,19	$\geq 0,18$
	Alunecare pe calcai	0,15	$\geq 0,13$

Marimi: 35-48