

VIRTUAL S3L FO SC SR ESD



DESCRIERE	NORM EN ISO 20345:2022 + A1:2024	REZULTAT	CERINTA
FETE: Respirabile si cu rezistenta ridicata la abraziune	5.4.3 Rezistenta la rupere 5.4.6 Permeabilitatea vaporilor de apa Coeficient	178 N 4,2 mg/cm2h 33,6 mg/cm2	≥ 60 N ≥ 0,8 mg/cm2h ≥ 15,0 mg/cm2
CAPTUSEALA CAPUTA: Material textil respirabil, rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	42 N No holes No holes 139,2 mg/cm2h 1113,9 mg/cm2	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm2h ≥ 20,0 mg/cm2
CAPTUSEALA STAIF: Material textil sintetic respirabil, rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	32 N No holes No holes 126,4 mg/cm2h 1011,6 mg/cm2	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm2h ≥ 20,0 mg/cm2
CAPTUSEALA: Material textil respirabil din microfibra gri, rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	32 N No holes No holes 15,2 mg/cm2h 122,6 mg/cm2	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm2h ≥ 20,0 mg/cm2
BOMBEU: Nemetalic din fibra de sticla 200J	5.3.2.6 Rezistenta la impact 5.3.2.7 Rezistenta la compresiune	16,0 mm 16,0 mm	≥ 14 mm ≥ 14 mm

LAMELA ANTIPERFORATIE: Non metalica, tesatura clasa PL	6.2.1.14 Rezistenta la perforare	PASS	Min. 1100 N
ACOPERIS DE BRANT: Detasabil, matlasat, brant antistatic	5.7.4.2 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat)	No holes No holes	12.800 cicluri 25.600 cicluri
TALPA EXTERIOARA: Poliuretan 3D, cu insert din E-TPU	5.8.3 Rezistenta la rupere 5.8.4 Rezistenta la abraziune 5.8.5 Rezistenta la flexare 5.8.6 Hidroliza 6.2.2.2 Antistatic 6.4.2 Rezistenta la uleiuri 5.3.5.2 Rezistenta la alunecare cu lauril sulfat de sodiu Alunecare calcai inainte Alunecare varf inapoi 6.2.10 Glicerina Alunecare calcai inainte Alunecare varf inapoi	8,4 kN/m 77 mm3 2,1 mm 2,5 mm uscat: 51,8 MΩ umed: 5,87 MΩ 1,3 % 0,34 0,39 0,22 0,25	≥ 8 kN/m ≤ 150 mm3 ≤ 4,0 mm ≤ 6,0 mm pass pass ≤ 12% ≥ 0,31 ≥ 0,36 ≥ 0,19 ≥ 0,22

MARIMI: 35 – 48

GREUTATE:

35	36	37	38	39	40	41	42	43	44	45	46	47	48
716	756	796	836	876	916	956	996	1036	1076	1116	1156	1196	1236

Marime	Cod EAN
35	9091001743356
36	9091001743363
37	9091001743370
38	9091001743387
39	9091001743394
40	9091001743400
41	9091001743417
42	9091001743424
43	9091001743431
44	9091001743448
45	9091001743455
46	9091001743462
47	9091001743479
48	9091001743486