

SOLANA S1 PL SC FO SR ESD



DESCRIERE	NORMA EN ISO 20345:2022 + A1:2024	REZULTAT	CERINTA
FETE: microfibra respirabila cu film anti-abraziune	5.4.3 Rezistenta la rupere 5.4.6 Permeabilitatea vaporilor de apa Coeficient	85 N 7,8 mg/cm ² h 64,2 mg/cm ²	≥60 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
CAPTUSEALA CAPUTA: material textil respirabil rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	46 N Fara gauri Fara gauri 66,2 mg/cm ² h 530,1 mg/cm ²	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
CAPTUSEALA STAIF: material textil respirabil rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	32 N Fara gauri Fara gauri 126,4 mg/cm ² h 1011,6 mg/cm ²	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
CAPTUSEALA: material textil respirabil rezistent la abraziune	5.5.2 Rezistenta la rupere 5.5.3 Rezistenta la abraziune (umed) Rezistenta la abraziune (uscat) 5.5.4 Permeabilitatea vaporilor de apa Coeficient	32 N Fara gauri Fara gauri 15,2 mg/cm ² h 122,6 mg/cm ²	≥ 15 N 25.600 cicluri 51.200 cicluri ≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
BOMBEU: fibra de sticla 200J	5.3.2.6 Rezistenta la impact 5.3.2.7 Rezistenta la compresiune	16,0 mm 16,0 mm	≥ 14 mm ≥ 14 mm
LAMELA ANTIPERFORATIE: clasa PL	6.2.1.1.3 Rezistenta la perforare	PASS	Min. 1100 N
TALPA: detasabila, respirabila, antistatica	5.7.4.2 Rezistenta la abraziune (uscat) Rezistenta la abraziune (umed)	FARA GAURI FARA GAURI	25.600 cicluri 12.800 cicluri
TALPA: 3D 2D cu insertie Etpu	5.8.3 Rezistenta la rupere 5.8.4 Rezistenta la abraziune 5.8.5 Rezistenta la flexare 5.8.6 Hidroliza 6.4.2 Rezistenta la uleiuri 6.2.10 Rezistenta la alunecare pe placi ceramice acoperite cu glicerina (inclinat spre calcai la 7°) (inclinat spre varf la 7°) 5.3.5.2 Rezistenta la alunecare pe placi ceramice spalate cu detergent (inclinat spre calcai la 7°) (inclinat spre varf la 7°) 6.2.2.2 Antistatic	8,4 kN/m 77 mm ³ 2,1 mm 2,5 mm 1,3 % 0,22 0,25 0,34 0,39 uscat: 51,8 MΩ umed: 5,87 MΩ	≥ 8 kN/m ≤ 150 mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,19 ≥ 0,22 ≥ 0,31 ≥ 0,36 0,1 ÷ 1000 MΩ 0,1 ÷ 1000 MΩ

GREUTATE:

35	36	37	38	39	40	41	42	43	44	45	46	47	48
663	722	781	840	899	958	1017	1076	1135	1194	1253	1312	1371	1430

EXENA SRL
via Breda 20
62012 Civitanova M. MC
ITALY

REA MC144207
Reg. Impr. Trib. MC 01336080435
C.F. e P. IVA 01336080435
Cap. Soc. € 25.823,00 i.v.

+39 0733 89 72 56
info@exena.com
amministrazione@pec.exena.it

exena.com