

LOLITE WHITE S3 SRC



DESCRIERE	NORMA EN ISO 20345:2011	RESULTAT CERINTE NORMA	
Fete: Microfibra DRY-WHITE, hidrofobizata	5.4.3 Rezistenta la sfasiere 5.4.6 Coeficient de Permeabilitatea la vapori de apa	153 N 1.9 mg/cm ² h 17.7 mg/cm ²	≥60 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
Captuseala caputa : Respirabila, rezistenta la abraziune, antibacterian	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Permeabiitatea vaporilor de apa Coeficient de permeabilitate	25 N Fara decupaj Fara decupaj 7.7 mg/cm ² h 62 mg/cm ² h	≥ 15 N 25.600 cicluri 12.800 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Captuseala staif: Tesatură respirabilă, rezistenta la abraziune	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Permeabiitatea vaporilor de apa Coeficient de permeabilitate	25 N Fara decupaj Fara decupaj 7.7 mg/cm ² h 62 mg/cm ² h	≥ 15 N 51.200 cicluri 25.600 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Bombeu de siguranta: Din material compozit rezistent la 200 J	5.3.2.3 Rezistenta la impact 5.3.2.4 Rezistenta la compresiune	14 mm 15.5 mm	≥ 14 mm ≥ 14 mm

Acoperis de brant: Detasabil,anatomic, antistatic,	5.7.4.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat)	Fara perforatii Fara perforatii	25.600 cicluri 12.800 cicluri
Talpa: PU 2D, antialunecare SRC	5.8.2 Rezistenta la sfasiere 5.8.3 Rezistenta la abraziune 5.8.4 Rezistenta la flexare 5.8.5 Hidroliza 6.4.2 Rezistenta la uleiuri 5.11 Rezistenta la alunecare pe placi ceramice spalate cu detergent Alunecare pe suprafata totala a talpii Alunecare pe calcai Rezistenta la alunecare pe placi din otel acoperite cu glicerina Alunecare pe suprafata totala a talpii Alunecare pe calcai	10.5 kN/m 58 mm ³ 2.5 mm 1.5 mm 1% 0,46 0,40 0,21 0,16	≥ 5 kN/m ≤250mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

MARIMI : 35-48

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519 C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207
www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

LOLITE WHITE S3 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Breathable texfiber	5.4.3 Tear strength	153 N	≥60 N
	5.4.6 Water vapor permeability	1,9 mg/cm ² h	≥ 0,8 mg/cm ² h
	Coefficient	17,7 mg/cm ²	≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance, antibacterial	5.5.1 Tear strength	25 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
	5.5.3 Water vapor permeability	7.7 mg/cm ² h	≥ 2,0 mg/(cm ² h)
	Coefficient	62.0 mg/cm ²	≥20,0 mg/cm ²
QUARTER LINING: breathable textile, abrasion resistance .	5.5.1 Tear strength	25 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No holes	51.200 cycles
	Abrasion resistance(Dry)	No holes	25.600 cycles
	5.5.3 Water vapor permeability	7.7 mg/cm ² h	≥ 2,0 mg/(cm ² h)
	Coefficient	62.0 mg/cm ²	≥20,0 mg/cm ²
SAFETY TOE CAP: Composite resistant to 200j force.	5.3.2.3 Impact resistance	14,0 mm	≥ 14 mm
	5.3.2.4 Compression resistance	15,5 mm	≥ 14 mm
FOOTBED: Removable, cushioned, antistatic insole	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
OUTSOLE PU 2D SRC, antislip	5.8.2 Tear strength	10.5 kN/m	≥ 5 kN/m
	5.8.3 Abrasion resistance	58mm ³	≤ 250 mm ³
	5.8.4 Flexing resistance	2.5 mm	≤ 4,0 mm
	5.8.5 Hydrolysis	1.5 mm	≤ 6,0 mm
	6.4.2 Oils resistance	1.0 %	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,46	≥ 0,32
	Heel slip	0,40	≥ 0,28
	Stainless steel plate on glycerin resistance		
	Flat slip	0,21	≥ 0,18
	Heel slip	0,16	≥ 0,13

SIZES: 35-48

MONDOPOINT: 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

Traducere din limba engleza - in conformitate cu documentul

EXENA
DECLARATIE DE CONFORMITATE UE
M22 -Vers. 00

Conform regulamentului (UE) 2016/425 – Anexa IX, **Exena srl** DECLARA
ca echipamentul individual de protectie si lotul respectiv de productie
descrie mai jos:

Articol: **LOLITE WHITE**

Lot: 65161



Este in conformitate cu standardul: EN ISO 20345:2011

Clasa: II

Categoria de marcaj: S3 SRC

Nr. certificat: F-130-04078-21

Data: 28.01.2021

EMIS DE: CIMAC – 0465

Civitanova Marche,

Aplicata parafa firmei EXENA S.R.L.

Sediul in Via Breda, 7/A

Civitanova Marche (MC), ITALIA ,

Sfârșitul traducerii

DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item

LOLITE WHITE

batch:

65161



conforms to the standard:

EN ISO 20345:2011

class:

II

marking category:

S3 SRC

certificate numb.:

F-130-04078-21

date:

28/01/2021

issued by:

CIMAC - 0465

Civitanova Marche

29/01/21

EXENA S.r.l.
Via Breda, 7/A - Zona Ind. le A
Tel. 0733 897256 Fax 0733 897519
62012 - CIVITANOVA MARCHE (MC)
P. IVA 01336080435

EXENA S.r.l.

Via Breda, 7 - Z.na Ind. A 62012 - CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib: MC N. 21676/1998 - CCIAA MC 22988

www.exena.it - info@exena.it - pec: amministrazione@pec.exena.it