

NOLE 20 S1P SRC



DESCRIERE	NORMA EN ISO 20345:2011	RESULTAT CERINTE NORMA	
Fete: Spalt bovina cu material textil si insertii reflectorizante	5.4.3 Rezistenta la sfasiere 5.4.6 Coeficient de Permeabilitatea la vapori de apa	175 N 2.7 mg/cm ² h 25.9 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
Captuseala caputa : Material textil perforat, rezistenta la abraziune ce asigura respiratia piciorului	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Permeabilitatea vaporilor de apa Coeficient de permeabilitate	45 N Fara decupaj Fara decupaj 4.7mg/cm ² h 40.5 mg/cm ² h	≥ 15 N 25.600 cicluri 12.800 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Captuseala stail: Tesatură respirabilă, rezistenta la abraziune	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Permeabilitatea vaporilor de apa Coeficient de permeabilitate	38 N Fara decupaj Fara decupaj 7.8 mg/cm ² h 63.3 mg/cm ² h	≥ 15 N 51.200 cicluri 25.600 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Bombeau de siguranta: Nemetalic, din policarbonat	5.3.2.3 Rezistenta la impact 5.3.2.4 Rezistenta la compresiune	15 mm 14.5 mm	≥ 14 mm ≥ 14 mm
Lamela antiperforare: Lamela nemetalica	5.7.1 Grosime 5.7.3 Absorbția de apa	3,6 mm 96 mg/cm ²	≥ 2 mm ≥ 70.0mg/cm ²

Acoperis de brant: Detasabil,anatomic, antistatic,	5.7.4.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat)	Fara perforatii Fara perforatii	25.600 cicluri 12.800 cicluri
Talpa: PU - TPU, antialunecare SRC	5.8.2 Rezistenta la sfasiere 5.8.3 Rezistenta la abraziune 5.8.4 Rezistenta la flexare 5.8.5 Hidroliza 6.4.2 Rezistenta la uleiuri 5.11 Rezistenta la alunecare pe placi ceramice spalate cu detergent Alunecare pe suprafata totala a talpii Alunecare pe calcai Rezistenta la alunecare pe placi din otel acoperite cu glicerina Alunecare pe suprafata totala a talpii Alunecare pe calcai	11 kN/m 64 mm ³ 2 mm 4 mm 2% 0,43 0,32 0,21 0,16	≥ 8 kN/m ≤150mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

MARIMI : 35-48

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519 C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207
www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

NOLE 20 S1P SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Suede leather, with reflex inserts	5.4.3 Tear strength	175 N	≥ 120 N
	5.4.6 Water vapor permeability	2,7mg/cm ² h	≥ 0,8 mg/cm ² h
	Coefficient	25,9 mg/cm ²	≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	45 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
	5.5.3 Water vapor permeability	4,7 mg/cm ² h	≥ 2,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistance.	Coefficient	40,5 mg/cm ²	≥ 20,0 mg/cm ²
	5.5.1 Tear strength	38 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No holes	51.200 cycles
	Abrasion resistance(Dry)	No holes	25.600 cycles
SAFETY TOE CAP: Non-metallic polycarbonate safety toe.	5.5.3 Water vapor permeability	7,8 mg/cm ² h	≥ 2,0 mg/cm ²
	Coefficient	63,3 mg/cm ²	≥ 20,0 mg/cm ²
	5.3.2.3 Impact resistance	15,0 mm	≥ 14 mm
PIERCE-RESISTANCE: Textile pierce proof footbed,	5.3.2.4 Compression resistance	14,5 mm	≥ 14 mm
	5.7.1. Thickness	3,6 mm	≥ 2,0 mm
FOOTBED: Removable, cushioned, antistatic insole.	5.7.3 Water absorption	96 mg/cm ²	≥ 70,0 mg/cm ²
	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
OUTSOLE: PU 2D, Antislip sole, SRC	5.8.2 Tear strength	11 kN/m	≥ 8 kN/m
	5.8.3 Abrasion resistance	64 mm ³	≤ 150 mm ³
	5.8.4 Flexing resistance	2,0 mm	≤ 4,0 mm
	5.8.5 Hydrolysis	4 mm	≤ 6,0 mm
	6.4.2 Oils resistance	2%	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,43	≥ 0,32
	Heel slip	0,32	≥ 0,28
	Stainless steel plate on glycerin resistance		
	Flat slip	0,21	≥ 0,18
	Heel slip	0,16	≥ 0,13

SIZES : 35-48; MONDOPOINT 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it

Traducere din limba engleza - in conformitate cu documentul

EXENA
DECLARATIE DE CONFORMITATE UE
M22 -Vers. 00

Conform regulamentului (UE) 2016/425 – Anexa IX, **Exena srl** DECLARA
ca echipamentul individual de protectie si lotul respectiv de productie
descrie mai jos:

Articol: **NOLE_20**

Lot: 70283



Este in conformitate cu standardul: EN ISO 20345:2011

Clasa: II

Categoria de marcaj: S1P SRC

Nr. certificat: F-130-04581-21

Data: **23.06.2021**

EMIS DE: CIMAC – 0465

Civitanova Marche,

Aplicata parafa firmei EXENA S.R.L.

Sediul in Via Breda, 7/A

Civitanova Marche (MC), ITALIA ,

Sfârșitul traducerii



DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item

NOLE 20

batch:

70283



conforms to the standard:

EN ISO 20345:2011

class:

II

marking category:

S1 P SRC

certificate numb.:

F-130-04581-21

date:

23/06/2021

issued by:

CIMAC - 0465

Civitanova Marche

~~EXENA S.r.l.
Via Breda, 7 - Z.na Ind. A
Tel. 0733 897256 fax 0733 897519
P. IVA 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988
R. IVA 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988~~

EXENA S.r.l.

Via Breda, 7 - Z.na Ind. A 62012 - CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it - info@exena.it - pec: amministrazione@pec.exena.it