

exena.

STELLAR S3L FO SC SR ESD



DESCRIPTION	NORM EN ISO 20345:2022 + A1:2024	RESULT	REQUIREMENT
UPPER: Water-repellent fabric with anti-abrasion film	5.4.3 Tear strength 5.4.6 Water vapor permeability Coefficient	122 N 15,7 mg/cm ² h 127,9 mg/cm ²	≥60 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.2 Tear strength 5.5.3 Abrasion resistance (Wet) Abrasion resistance (Dry) 5.5.4 Water vapor permeability Coefficient	42 N No holes No holes 139,2 mg/cm ² h 1113,9 mg/cm ²	≥ 15 N 25.600 cycles 51.200 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistance mesh	5.5.2 Tear strength 5.5.3 Abrasion resistance (Wet) Abrasion resistance (Dry) 5.5.4 Water vapor permeability Coefficient	32 N No holes No holes 126,4 mg/cm ² h 1011,6 mg/cm ²	≥ 15 N 25.600 cycles 51.200 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
COUNTER LINING:	5.5.2 Tear strength 5.5.3 Abrasion resistance (Wet) Abrasion resistance (Dry) 5.5.4 Water vapor permeability Coefficient	32 N No holes No holes 15,2 mg/cm ² h 122,6 mg/cm ²	≥ 15 N 25.600 cycles 51.200 cycles ≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
SAFETY TOE CAP: Fiberglass 200J	5.3.2.6 Impact resistance 5.3.2.7 Compression resistance	16,0 mm 16,0 mm	≥ 14 mm ≥ 14 mm

EXENA SRL
via Breda 20
62012 Civitanova M. MC
ITALY

REA MC144207
Reg. Impr. Trib. MC 01336080435
C.F. e P. IVA 01336080435
Cap. Soc. € 25.823,00 i.v.

+39 0733 89 72 56
info@exena.com
amministrazione@pec.exena.it

exena.com

PIERCE-RESISTANCE: Class PL anti-perforation fabric	6.2.1.1.3 Resistance to perforation	PASS	Min.1100 N
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance (dry)	NO HOLES	25.600 cycles
	Abrasion resistance (wet)	NO HOLES	12.800 cycles
OUTSOLE : 2 density polyurethane with Etpu insert	5.8.3 Tear strength	8,4 kN/m	≥ 8 kN/m
	5.8.4 Abrasion resistance	77 mm ³	≤ 150 mm ³
	5.8.5 Flexing resistance	2,1 mm	≤ 4,0 mm
	5.8.6 Hydrolysis	2,5 mm	≤ 6,0 mm
	6.4.2 Oils resistance	1,3 %	≤ 12%
	6.2.10 Slip resistance on ceramic with glycerin		
	(tilted towards the heel of 7°)	0,22	≥ 0,19
	(tilted towards the tip of 7°)	0,25	≥ 0,22
	5.3.5.2 Slip resistance on ceramic with cleaning agent		
	(tilted towards the heel of 7°)	0,34	≥ 0,31
	(tilted towards the tip of 7°)	0,39	≥ 0,36
	6.2.2.2 Antistatic	dry: 51,8 MΩ wet: 5,87 MΩ	0,1 ÷ 1000 MΩ 0,1 ÷ 1000 MΩ

SIZES: 35 – 48

WEIGHT:

34	35	36	37	38	39	40	41	42	43	44	45	46	47	48
	740	799	858	917	976	1035	1094	1153	1212	1271	1330	1389	1448	1507